

SELECTION & SPECIFICATION DATA

| | |
|---|--|
| Type | Non-fibered Asphalt Emulsion |
| Description | A blend of selected mineral fillers and emulsified asphalts that provides an excellent base emulsion for further compounding. |
| Features | <ul style="list-style-type: none"> • Water-based with low VOCs • Very stable - no settling or separation • Environmentally friendly • Readily accepts latex modification |
| Uses | <ul style="list-style-type: none"> • Sizing emulsion • Base emulsion |
| Color | Black |
| Finish | Matte |
| Primer | Self-priming |
| Dry Film Thickness (DFT) | 3 – 6 mils per coat |
| Solids Content | 60% by weight 61% by volume |
| Theoretical Coverage Rate | 946 square feet per gallon at 1 mil DFT |
| Maximum Dry Temperature Resistance | 200°F (93.3°C) |
| Limitations | Protect from freezing Not for immersion service |

SUBSTRATES & SURFACE PREPARATION

| | |
|------------------------------------|--|
| All | Surfaces must be clean and dry. Remove all dirt, dust, oil and all other contaminants. |
| Previously Painted Surfaces | Consult with ErgonArmor Technical Service Department. |

MIXING & THINNING

| | |
|-----------------|---|
| Mixing | Not required |
| Thinning | Generally not required. Product is thixotropic and will thin under shear. If a reduction in static viscosity is desired, agitate to thin. The addition of water is not recommended. |
| Ratio | Single component |

APPLICATION GUIDELINES

| | |
|--------------------------|--|
| Spray Application | Ertech 3000SBC is designed for spray application using airless equipment. |
| Airless Spray | For best results under a wide variety of spray conditions, a 30:1 or higher ratio pump is recommended. |
| Tip Size | A 0.021 in orifice tip size is recommended. |
| Hose L/D | 200 ft (max) x 3/8 in diameter |
| Whip L/D | 6 ft (max) x 1/4 in diameter |
| Pump Packings | PTFE/UHMWP packings in the spray pump are recommended. |
| Film Thickness | A film thickness of up to 10 mils wet can be achieved on vertical surfaces without sagging. |
| Brush/Roller | Ertech 3000SBC can be brush or roller applied. |
| Temperature | Use in temperatures of 50°F (10°C) or higher for best performance. |
| Dry-To-Touch | 2 – 4 hours at 77°F (25°C). Dry times are decreased with air movement over the coating. |
| Full Cure | 24 – 48 hours at 77°F (25°C). Cure times are decreased with air movement over the coating. |

CLEANUP & SAFETY

| | |
|--------------------|--|
| Cleanup | Tools and hands should be cleaned with soap and water before the emulsion sets. Dried material can be cleaned with mineral spirits. Spray equipment should be flushed with soapy water then fresh water for short periods of non-use. For longer periods of non-use, a final flush using mineral spirits is recommended. |
| Safety | Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using. |
| Ventilation | Use in well ventilated areas. |

PACKAGING, HANDLING & STORAGE

| | |
|--|--|
| Shelf Life | 6 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers. |
| Package Sizes & Shipping Weight | 5 gallon pail – 44 lbs (20 kg) 16 gallon keg – 141 lbs (64 kg) 53 gallon drum – 475 lbs (215 kg) 275 gallon IBC tote – 2390 lbs (1084 kg) |
| Storage Temperature | 50°F – 110°F (10°C – 43°C) |
| Storage | Protect from freezing. Do not store product outside. Store indoors. |

TYPICAL PHYSICAL PROPERTIES

| | |
|--|-----------------|
| Density ASTM D1475-13 | 8.2 lbs/gal |
| Solids by weight ASTM D5201-05a | 60% |
| Solids by volume ASTM D5201-05a | 61% |
| Specific gravity | 0.98 |
| Dry-to-touch, 77°F (25°C) ASTM D5895-96 | 2 – 4 hours |
| Full cure, 77°F (25°C) | 24 – 48 hours |
| Viscosity, 77°F (25°C) ASTM D2983-19 | 650 cps |
| Resistance to oils, greases & solvents | Poor |
| VOC ASTM D3960-05 | 0.2 lbs/gal max |

Rev 01/2020

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.