

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Carbon-filled vinyl ester tile grout
<b>Description</b>	Pennchem CIP Tile Grout is a 3-component carbon-filled vinyl ester tile and paver floor grout.
<b>Uses</b>	Brick and tile flooring in: <ul style="list-style-type: none"> <li>• CIP and COP areas in food processing facilities</li> <li>• Breweries and distilleries</li> <li>• Bottling plants</li> <li>• Meat and poultry processing plants</li> <li>• Pharmaceutical plants</li> <li>• Chemical process facilities</li> </ul>
<b>Features</b>	<ul style="list-style-type: none"> <li>• Resistant to hot 50% sodium hydroxide</li> <li>• Resistant to oxidizing sanitizers containing bleach, chlorine, nitric acid, acetic acid and hydrogen peroxide</li> <li>• Easy to mix and apply</li> <li>• High bond strength</li> </ul>
<b>Limitations</b>	<ul style="list-style-type: none"> <li>• Not suitable for vertical wall tile applications.</li> <li>• Not water washable.</li> <li>• Use care in operating food plants to protect product from grout odor until it has fully cured.</li> <li>• Not for use beyond its chemical resistance or thermal capabilities. Consult ErgonArmor with specific questions.</li> </ul>

## INSTALLATION GUIDANCE

<b>Reference Specifications</b>	CES-309 Installation of direct bond tile floors
<b>Installation Conditions</b>	Pennchem CIP Tile Grout is formulated for ideal handling at 70°F (21°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure. Bricks or tiles must be clean, dry and neutral pH.
<b>Ratio</b>	1.0 resin: 0.016 hardener: 1.67 filler by weight. Mix ratio may be varied slightly by adjusting filler loading to suit individual tile setter preferences.
<b>Mixing</b>	Pour measured quantity of resin into clean, dry mixing vessel. Slowly add measured quantity of hardener to resin and mix thoroughly. Add filler and mix until filler is thoroughly wetted and grout is creamy, free of lumps and trowelable.
<b>Work Life</b>	30-45 minutes at 70°F (21°C)  Work life is shorter at higher temperatures. A larger volume of mixed material will have a shorter work life than a smaller volume.
<b>Cleanup</b>	Methyl ethyl ketone (MEK)

## CURE TIME

<b>Brick or Tile Temperature</b>	<b>Initial Set</b>	<b>Full Cure</b>
70°F (21°C)	1-1.5 hours	36 hours

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
<b>Ventilation</b>	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

**PACKAGING & ESTIMATING**

Product	Code	Packaging
Pennrowel Vinyl Ester Resin Clear	29464	43 lb (5 gal) pail
CHP Hardener	19552	0.75 lb (11.2 fl oz) bottle
Pennrowel L/F Filler Carbon	29446	36 lb bag

A 116 lb (1.18 ft<sup>3</sup>) unit consists of 1 x 43 lb pail of resin, 1 x 0.75 lb bottle of hardener and 2 x 36 lb bags of filler.

**Theoretical Coverage** Consumption will vary based on tile size and joint width. Consult estimating guide CES-145 or ErgonArmor for assistance.

**Storage & Shelf Life** Maintain products in original packaging and sealed until ready for use. Estimated shelf life of Pennrowel Vinyl Ester Resin is 4-6 months and estimated shelf life of CHP Hardener and Pennrowel L/F Filler Carbon is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

**TYPICAL PHYSICAL PROPERTIES**

Property	Typical Value
Color	Black
Density, ASTM C138	98 lb/ft <sup>3</sup> (1,570 kg/m <sup>3</sup> )
Compressive strength, ASTM C579	>15,000 psi (103 MPa)
Tensile strength, ASTM C307	>1,500 psi (10.3 MPa)
Bond to tile, pull blocks	>1,200 psi (8.3 MPa)
Water absorption, ASTM C413	0.2%
Adhesion to concrete, ASTM C321	Exceeds strength of concrete
Maximum service temperature	225°F (107°C)

Rev 01/2021

**TERMS AND CONDITIONS OF SALE**

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).