

SELECTION & SPECIFICATION DATA

Type	Vinyl ester tile grout
Description	Pennchem Tile Grout is a 2-component vinyl ester tile and paver floor grout.
Uses	Brick and tile flooring in: <ul style="list-style-type: none"> • CIP areas in food processing facilities • Breweries and distilleries • Bottling plants • Meat and poultry processing plants • Pharmaceutical plants • Chemical process facilities
Features	<ul style="list-style-type: none"> • Resists oxidizing chemicals, mineral and organic acids, some organic solvents • 2 component – resin and reactive powder • Easy to mix and apply • Rapid strength development • Cure accelerator available for low temperature installation conditions
Limitations	<ul style="list-style-type: none"> • Not suitable for vertical wall tile applications. • Not water washable. • Use care in operating food plants to protect product from grout odor until it has fully cured. • Not for use beyond its chemical resistance or thermal capabilities. Consult ErgonArmor with specific questions.

INSTALLATION GUIDANCE

Reference Specifications	CES-309 Installation of direct bond tile floors
Installation Conditions	Pennchem Tile Grout is formulated for ideal handling at 70°F (21°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure. Add Pennchem Initiator for temperatures between 35°F (2°C) and 50°F (10°C). Bricks or tiles must be clean, dry and neutral pH.
Ratio	1.0 resin: 2.4 powder by weight. Mix ratio may be varied slightly by adjusting filler loading to suit individual tile setter preferences.
Mixing	Pour measured quantity of resin into clean, dry mixing vessel. Add Pennchem Initiator to resin if using. Slowly add measured quantity of powder to resin and mix thoroughly. Mix until powder is thoroughly wetted and grout is creamy, free of lumps and trowelable.
Work Life	55 minutes at 70°F (21°C) Work life is shorter at higher temperatures. A larger volume of mixed material will have a shorter work life than a smaller volume.
Cleanup	Methyl Ethyl Ketone (MEK)

CURE TIME

Brick or Tile Temperature	Initial Set	Remove Grout Residue	Full Cure
70°F (21°C)	1 hour	8 hours	36 hours

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

PACKAGING & ESTIMATING

Product	Code	Packaging
Pennchem Resin	26824	40 lb (18.1 kg) pail
Pennchem Powder	26823	50 lb (22.7 kg) bag
Pennchem Initiator	19524	32 oz bottle

A 140 lb (1.35 ft³) unit of Pennchem Tile Grout consists of 1 x 40 lb (18.1 kg) pail of resin and 2 x 50 lb (22.7 kg) bags of powder.

For low temperature use or faster work life and set time, add 2.0 to 3.0 fl oz of Pennchem Initiator to a pail of Pennchem Resin before adding powder.

Theoretical Coverage

Consumption will vary based on tile size and joint width. Consult estimating guide CES-145 or ErgonArmor for assistance.

Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life of resin is 4-6 months when stored in a dry area at 70°F (21°C). Estimated shelf life of powder is 12 months. Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	White
Density, ASTM C138	104 lb/ft ³ (1,666 kg/m ³)
Compressive strength, ASTM C579	>10,000 psi (69 MPa)
Modulus of elasticity, ASTM C580	0.96 x 10 ⁶ psi (6,620 MPa)
Linear shrinkage, ASTM C531	0.2%
Bond strength, ASTM C321	Exceeds strength of concrete Exceeds strength of brick
Tensile strength, ASTM C307	>1,500 psi (10.3 MPa)
Flexural strength, ASTM C453	>3,000 psi (20.7 MPa)
Maximum service temperature	225°F (107°C)

Rev 05/2024

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.