

SELECTION & SPECIFICATION DATA

Type	Epoxy Primer
Description	Novocoat SC1100 Primer/Sealer FC is a penetrating, moisture-tolerant epoxy primer designed to cure under cool conditions. It seals porous concrete surfaces to prevent outgassing and associated blisters and pinholes and promotes adhesion to a variety of finish coats. Standard grade Novocoat SC1100 Primer/Sealer is available for warm application conditions.
Features	<ul style="list-style-type: none"> • No VOC • Low temperature cure • Exceptional wetting characteristics • Low stress, highly flexible film • Adheres to damp concrete • Green concrete primer (7+ days)
Uses	<ul style="list-style-type: none"> • Concrete primer/sealer • Universal binder for trowel-applied flooring • Binder for concrete resurfacing mortar
Colors	Amber clear
Finish	Gloss
Dry Film Thickness (DFT)	3 - 5 mils per coat
Solids Content	99 - 100% by volume
Limitations	Will lose gloss, discolor, and chalk in sunlight.

SUBSTRATES & SURFACE PREPARATION

Concrete or Concrete Masonry Unit (CMU)	Substrate must be clean, dry and free of contaminants. Concrete must be cured a minimum of 7 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with SSPC-SP 13/NACE 6. Required surface profile is CSP 1 as stand-alone coating, CSP 3-5 under a topcoat. Voids in concrete surfaces may require filling. Mortar joints should be cured a minimum of 15 days.
--	---

MIXING & THINNING

Ratio	2A:1B by volume
Mixing	Thinning not required. Premix parts A and B separately then combine and power mix at a slow speed for 2 minutes.
Pot Life	100 minutes at 40°F (4°C) 47 minutes at 70°F (21°C) Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.
Cleanup	MEK or Acetone

APPLICATION GUIDELINES

Spray Application	The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss, and Graco.
Airless Spray Single Leg or Hot Pot	Pump Size: 30:1 or greater Hose Length: 200 ft x 3/8-inch ID Whip Length: 10 ft x 1/4-inch ID Heat parts A and B separately to 75°F - 85°F (24°C - 29°C) before mixing so product atomizes properly in delivering paint to the substrate.
Brush	Medium bristle brush. Be aware of work life when using brush or roller application.
Roller	Short-nap synthetic roller cover with phenolic core.

CURE SCHEDULE & RECOAT WINDOW

SUBSTRATE	MINIMUM RECOAT	MAXIMUM RECOAT
40°F (4°C)	8 hours	48 hours
59°F (15°C)	5 hours	36 hours
70°F (21°C)	4 hours	24 hours

For other installation conditions, consult ErgonArmor for guidance.

PACKAGING, ESTIMATING & HANDLING

ITEM#	PRODUCT	PACKAGING
M-SC1100F-SMKT-01	Novocoat SC1100 Primer/Sealer FC - Part A Resin - Part B Hardener	0.9 gal (3.4 L) Kit 5.7 lbs (2.6 kg) Pail 2.5 lbs (1.1 kg) Jerrican
M-SC1100F-LGKT-01	Novocoat SC1100 Primer/Sealer FC - Part A Resin - Part B Hardener	4.2 gal (16.3 L) Kit 27 lbs (12 kg) Pail 12 lbs (5.4 kg) Pail
M-SC1100A-DRUM-01	Novocoat SC1100 Primer/Sealer - Part A Resin	50 gal (189 L) Drum
M-SC1101B-DRUM-01	Novocoat SC1100 Primer/Sealer FC - Part B Hardener	50 gal (189 L) Drum

Theoretical Coverage

Concrete: 320 - 530 square feet per gallon at 3 - 5 wet mils per coat. Allow for loss in mixing and application.

Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult ErgonArmor Technical Service.

SAFETY

Safety

Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

Ventilation

Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	SUBSTRATE	VALUE
Dry pull-off adhesion ASTM D4541	Blasted steel 1 coat	>2,500 psi (17 MPa)
Dry pull-off adhesion ASTM D4541	Concrete	>500 psi (3.4 MPa) Concrete failure

SERVICE TEMPERATURE

SERVICE	MAXIMUM TEMPERATURE
Dry, continuous	176°F (80°C)
Dry, non-continuous	203°F (95°C)

Temperature limitations will vary with chemical exposure. Consult ErgonArmor Technical Service for guidance.

Rev. 08/2024

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.